

Amendments to the Claims:

The following listing of claims replaces all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (currently amended) A process for producing an organic-inorganic hybrid glassy material, the process comprising at least the three sequential steps of:

producing a gel body by a sol-gel method in which at least one kind of a silicon alkoxide containing a phenyl group is used as a sol-gel raw material;

melting the gel body by heating into a melt; and

aging the melt at a temperature of from 30°C to 400°C for a period of time of 5 minutes or longer.

2. (previously presented) A process for producing an organic-inorganic hybrid glassy material as claimed in claim 1, wherein a structure of the gel body contains a unit represented by the formula of $\text{Ph}_n\text{SiO}_{(4-n)/2}$ where Ph represents a phenyl group and n represents a natural number selected from 1, 2 and 3.

3. (canceled)

4. (previously presented) A process for producing an organic-inorganic hybrid glassy material as claimed in claim 1, wherein the melting step by heating is conducted at a temperature of from 30°C to 400°C.

5-22. (canceled)

23. (previously presented) A process for producing an organic-inorganic hybrid glassy material, the process comprising the sequential steps of:

producing a gel body by a sol-gel method in which at least one kind of a silicon alkoxide containing a phenyl group is used as a sol-gel raw material;

mixing the gel body with a substance obtained by a non-aqueous acid-base reaction method to prepare a mixture;

melting the mixture by heating into a melt; and

aging the melt at a temperature of from 30°C to 400°C for a period of time of 5 minutes or longer.

24. (currently amended) A process for producing an organic-inorganic hybrid glassy material as claimed in claim 23, wherein the gel body produced by the sol-gel method contains $\text{RSiO}_{3/2}$ or R_2SiO_2 [D] wherein R represents a phenyl group [D] .

25. (currently amended) A process for producing an organic-inorganic hybrid glassy material as claimed in claim 23 or 24, wherein the substance obtained by the non-aqueous acid-base reaction method contains R_2SiO_2 [D] wherein R represents a methyl or ethyl group [D] , P_2O_5 and SnO .

26. (previously presented) A process for producing an organic-inorganic hybrid glassy material as claimed in claim 23, wherein the melting step by heating is conducted at a temperature of from 30°C to 400°C.

27-29. (canceled)

30. (new) A process for producing an organic-inorganic hybrid glassy material, the process comprising the sequential steps of:

producing a gel body by a sol-gel method in which a phenyltrialkoxysilane and a second silane are used as sol-gel raw materials, wherein the second silane is selected from the group consisting of alkylalkoxysilanes and diphenyldialkoxysilanes;

melting the gel body by heating into a melt; and

aging the melt at a temperature of from 30°C to 400°C for a period of time of 5 minutes or longer.

31. (new) A process according to claim 30, wherein:

the phenyltrialkoxysilane is phenyltriethoxysilane; and

the diphenyldialkoxysilane is diphenyldiethoxysilane or the alkylalkoxysilane is selected from the group consisting of methyltriethoxysilane, dimethyldiethoxysilane, diethyldiethoxysilane, and ethyltriethoxysilane.

32. (new) A process according to claim 30, wherein:

the phenyltrialkoxysilane is phenyltriethoxysilane; and

the second silane is a dialkyldialkoxysilane.

33. (new) A process according to claim 32, wherein the dialkyldialkoxysilane is dimethyldiethoxysilane or diethyldiethoxysilane.

34. (new) A process according to claim 30, wherein:

the phenyltrialkoxysilane is phenyltriethoxysilane; and

the second silane is a diphenyldialkoxysilane.

35. (new) A process according to claim 34, wherein the diphenyldialkoxysilane is diphenyldiethoxysilane.